

TECHNICAL SPECIFICATION















Series: **Precious Stone Matt** ;

Article: **Beige, Bianco, Greige** ;

Sizes (cm)/Thicknesses (mm): **60x120/11(Rectified)**;

Product group: **B1a (Water absorption $\leq 0,5$ %)**;

Surface: **GLAZED (GL)**;

TECHNICAL CHARACTERISTICS		TEST METHOD	ISO STANDARD	BELLISSIMO STANDARD
	Deviation in Length & Width	ISO 10545 - 2	$\pm 0.6\%$	$\pm 0.1\%$
	Deviation in thickness	ISO 10545 - 2	$\pm 5\%$	$\pm 4\%$
	Straightness of sides	ISO 10545 - 2	$\pm 0.5\%$	$\pm 0.1\%$
	Rectangularity	ISO 10545 - 2	$\pm 0.5\%$	$\pm 0.5\%$
	Surface flatness	ISO 10545 - 2	$\pm 0.5\%$	$\pm 0.15\%$
	Surface Quality	ISO 10545 - 2	A min 95 % of the tiles are to be free from visible	99.5 %
	Water Absorption	ISO 10545 - 3	$< 0.5\%$	$\leq 0.1\%$ FOR UGL $\leq 0.5\%$ FOR GL
	Breaking Strength (S)	ISO 10545 - 4	$\geq 1300N$	$\geq 1300N$
	Modulus of Rupture	ISO 10545 - 4	$\geq 35 N/m^2$	$\geq 45 N/m^2$
	Deep Abrasion	ISO 10545 - 5	$< 175 N/m^3$	$\leq 145 N/m^3$
	Frost Resistance	ISO 10545 - 12	Resistance	Resistance
	Chemical Resistance	ISO 10545 - 13	Resistance	Resistance
	Scratch Hardness	ISO 363 - 13	≥ 4 moh's	≥ 5 moh's
	Stain Resistance	ISO 10545 - 14	Resistance	Class 5*

" * " Vary according to surface finish like natural polish & lapata

TECHNICAL SPECIFICATION OF VITRIFIED TILES















Series: **Precious Stone Lux;**

Article: **Beige, Bianco, Greige;**

Sizes (cm)/Thicknesses (mm): **60x120/11 (Rectified);**

Product group: **B1a (Water absorption $\leq 0,5$ %);**

Surface: **GLAZED (GL);**

TECHNICAL CHARACTERISTICS	TEST METHOD	ISO STANDARD	BELLISSIMO STANDARD
 Deviation in Length & Width	ISO 10545 - 2	$\pm 0.6\%$	$\pm 0.1\%$
 Deviation in thickness	ISO 10545 - 2	$\pm 5\%$	$\pm 4\%$
 Straightness of sides	ISO 10545 - 2	$\pm 0.5\%$	$\pm 0.1\%$
 Rectangularity	ISO 10545 - 2	$\pm 0.5\%$	$\pm 0.5\%$
 Surface flatness	ISO 10545 - 2	$\pm 0.5\%$	$\pm 0.15\%$
 Surface Quality	ISO 10545 - 2	A min 95 % of thr tiles are to be free from visible	99.5 %
 Water Absorption	ISO 10545 - 3	$< 0.5\%$	$\leq 0.1\%$ FOR UGL $\leq 0.5\%$ FOR GL
 Breaking Strength (S)	ISO 10545 - 4	$\geq 1300N$	$\geq 1300N$
 Modulus of Rupture	ISO 10545 - 4	$\geq 35 N/m^2$	$\geq 45 N/m^2$
 Deep Abrasion	ISO 10545 - 5	$< 175 N/m^3$	$\leq 145 N/m^3$
 Frost Resistance	ISO 10545 - 12	Resistance	Resistance
 Chemical Resistance	ISO 10545 - 13	Resistance	Resistance
 Scratch Hardness	ISO 363 - 13	≥ 4 moh's	≥ 5 moh's
 Stain Resistance	ISO 10545 - 14	Resistance	Class 5*

" * " Vary according to surface finish like natural polish & lapata