

## **Tender specifications**

### **BLEND STONE collection**

Supply of Cotto d'Este porcelain stoneware tiles for walls and floors.

#### **Product characteristics**

Cotto d'Este full body porcelain stoneware tiles, unglazed, composed of a very fine mixture of quality clay with the addition of feldspar, quartz and kaolin, manufactured by dry pressing of atomized powders and subsequently sintered by industrial firing at temperatures above 1200°C.

The complete vitrification of the tiles allows for a compact, non-absorbent, frost-proof product, resistant to bending, impacts, staining, chemical attack and thermal shock.

#### Compliance with EN 14411-G / ISO 13006-G

The Blend Stone collection is in compliance with the regulations required for first quality products in Italy and Europe UNI EN 14411-G and internationally through ISO 13006-G.

#### Quality and environmental certifications

The conservation of the product characteristics is guaranteed by the Quality Management System put into practice by Cotto d'Este in its plants and certified in accordance with UNI EN ISO 9001.

The collection is manufactured in plants with UNI EN ISO 14001 certified Environmental Management Systems (internationally recognized standard) and EMAS (Regulation 1221/09 - eco-management and audit community system). The collection helps to meet the criteria for obtaining LEED credits. The content of "pre-consumer" recycled material is 40%,

as certified by a qualified external body (LEED V4 Regulations - MR Credit). The product contains no VOC (volatile organic compounds) and has obtained the GREENGUARD GOLD certification. The Environmental Product Declaration (EPD) is available, this tool communicates clearly the environmental performances of the Blend Stone collection based on its Life Cycle Assessment (LCA).

#### **Antibacterial properties**

Thanks to Protect antibacterial technology, the tiles from the Blend Stone collection have continuous, effective and durable protection against the proliferation of bacteria, tested and certified in accordance with ISO 22196 and ASTM E3031. (Not for SABBIATA & BOCCIARDATA surfaces)

Commercial description of the product					
Company	COTTO D'ESTE (Panariagroup Industrie Ceram	COTTO D'ESTE (Panariagroup Industrie Ceramiche S.p.A.)			
Collection	BLEND STONE	BLEND STONE			
Colours	CLEAR, LIGHT, MID, DEEP	CLEAR, LIGHT, MID, DEEP			
	90x180cm NATURALE, LAPPATA				
	90x90cm NATURALE, LAPPATA, SABBIATA	90x90cm BOCCIARDATA 20mm			
C!	120x120cm NATURALE, LAPPATA, SABBIATA				
Sizes	60x120cm NATURALE, LAPPATA, SABBIATA	60X120cm BOCCIARDATA 20mm			
	60x60cm NATURALE, LAPPATA, SABBIATA				
	30X60cm NATURALE, LAPPATA, SABBIATA				
Surfaces	NATURALE, LAPPATA, SABBIATA, BOCCIARDA	NATURALE, LAPPATA, SABBIATA, BOCCIARDATA			
Edges	RECTIFIED (RECT)	RECTIFIED (RECT)			
Thickness	14mm/20mm	14mm/20mm			























# **Tender specifications**

### **BLEND STONE Collection**

#### **Technical features**

Product type: full body porcelain stoneware (UGL)

According to: ISO 13006-G (Group Bla), EN 14411-G (Group Bla)

Technical features		Test method	Required values ISO 13006-G, EN 14411-G	Average values BLEND STONE
Water absorption		ISO 10545-3	≤ 0,5 %	0,05 %
Breaking strength (S)		ISO 10545-4	≥ 1300 N	6080 N (14mm) 13600 N (20mm)
Modulus of rupture		ISO 10545-4	≥ 35 N/mm <sup>2</sup>	50 N/mm <sup>2</sup>
Deep abrasion resistance		ISO 10545-6	≤ 175mm³	143mm <sup>3</sup>
Linear thermal expansion		ISO 10545-8	No provision	$\alpha \le 7 \cdot 10^{-6}  {}^{\circ}\text{C}^{-1}$
Stain resistance		ISO 10545-14	Class 3 Min.	5 RESISTANT
Chemical resistance (*)		ISO 10545-13	As indicated by manufacturer	LA, HA RESISTANT
Frost resistance		ISO 10545-12	No alteration	RESISTANT
	Lenght and width	ISO 10545-2	± 0,3 %, max ± 1 mm	COMPLIANT
ons	Straightness of sides	ISO 10545-2	± 0,3 %, max ± 0,8 mm	COMPLIANT
Dimensions	Rectangularity	ISO 10545-2	± 0,3 %, max ± 1,5 mm	COMPLIANT
Dirr	Warpage	ISO 10545-2	± 0,4 %, max ± 1,8 mm	COMPLIANT
	Thickness	ISO 10545-2	± 5 %, max ± 0,5 mm	COMPLIANT
Slip resistance		DIN 51130	-	R10 (NATURALE) R11 (SABBIATA) R12 (BOCCIARDATA 20mm)
		DIN 51097	-	A+B (NATURALE) A+B+C (SABBIATA, BOCCIARDATA 20mm)
		BCR-TORTUS	-	$\mu$ > 0,40 (NATURALE, SABBIATA, BOCCIARDATA 20mm)
		ANSI A 326.3	-	DCOF≥0.42 (NATURALE, SABBIATA, BOCCIARDATA 20mm)
		AS-NZS 4586	-	P3 (NATURALE) P4 (SABBIATA, BOCCIARDATA 20mm)
		BS 7976-2	-	PTV 36+ Wet SI.96 (NATURALE) PTV 36+ Wet SI.55 & SI.96 (SABBIATA, BOCCIARDATA 20mm)
		UNE 41901 EX	-	Clase 2 (NATURALE) Clase 3 (SABBIATA, BOCCIARDATA 20mm)
Shade variation		ANSI A 137.1	As indicated by manufacturer	V2
Fire reaction		EN 13823	CPR (UE) 305/2011, 2000/147/CE, UNI EN 13501-1	Class A1 (wall)
		EN 9239-1		Class A1 <sub>fl</sub> (floor)
Thermal conductivity		EN 12524	-	λ = 1,3 W/m °K
Recommended minimum joint (**)		Indoor	-	2mm
		Outdoor	-	5-6mm Approx

 $<sup>(\</sup>ensuremath{^*}\xspace)$  Excluding hydrofluoric acid and its derivatives.

<sup>(\*\*)</sup> The width of grout joints must be established by the installation supervisor, unless grout widths are regulated by national laying standards.



















