















CARATTERISTICHE TECNICHE

TECHNICAL FEATURES . CARACTÉRISTIQUES TECHNIQUES . TECHNISCHE EIGENSCHAFTEN . ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ

GRES PORCELLANATO SMALTATO COLORATO IN MASSA - ISO 13006 Bia GL GLAZED PORCELAIN STONEWARE WITH COLOURED BODY . GRÈS CÉRAME ÉMAILLÉ COLORÉ DANS LA MASSE GLASIERTES FEINSTEINZEUG IN DER MASSE GEFÄRBT . ГЛАЗУРОВАННЫЙ КЕРАМОГРАНИТ, ОКРАШЕННЫЙ ПО ВСЕЙ ТООЛЩИНЕ

	<p>Aspetto superficiale Surface appearance Aspect superficiel Oberflächenbeschaffenheit Вид поверхности</p>	<p>≥ 95%</p>	<p>Conforme Compliant Conforme Konform Соответствует</p>																								
	<p>Lunghezza e larghezza Length and width Longueur et largeur Länge und Breite Длина и ширина</p>	<p>Deviazione valore medio % rispetto a dimensione di fabbricazione. Deviation of the average size for each tile from the work size (%). Écart dimensionnel moyen en % par rapport aux dimensions de fabrication. Abweichung des Durchschnittswertes in % hinsichtlich der Produktionsgröße. Отклонение средн. значения, % от производственных размеров > 410 cm2 +/- 0,6% - ≤ 410 cm2 +/- 0,75%</p>	<p>± 0,5% ± 1,5 mm</p>																								
	<p>Rettilinearità degli spigoli Straightness of sides Rectitude des arêtes Kantengeradheit Прямолинейность кромок</p>	<p>Deviazione valore medio % rispetto a dimensione di fabbricazione. Deviation of the average size for each tile from the average size to the 10 test specimens (%). Écart de valeur moyenne unitaire % en rapport à la valeur moyenne de 10 échantillons mesurés. Abweichung des Durchschnittswertes der einzelnen Fliesen in % hinsichtlich des Durchschnitts von 10 getesteten Mustern. Отклонение средн. значения, отдельной плитки относительно средн. значения 10 измеренных образцов +/- 0,5%</p>	<p>± 0,5% ± 1,5 mm</p>																								
	<p>Spessore / Thickness / Epaisseur/Stärke / Толщина</p>	<p>+/- 5%</p>	<p>± 5% ± 0,5 mm</p>																								
	<p>Ortogonalità Rectangularity Orthogonalité Rechtwinkligkeit Ортогональность</p>	<p>+/- 0,5%</p>	<p>± 0,3% ± 1,5 mm</p>																								
	<p>Planarità Surface flatness Planéité Ebenflächigkeit Плоскостность</p>	<p>+/- 0,5%</p>	<p>± 0,5% ± 1,5 mm</p>																								
	<p>Assorbimento d'acqua Water absorption Absorption d'eau Wasseraufnahme Водопоглощение</p>	<p>≤ 0,5% GRUPPO Bia GL</p>	<p>E ≤ 0,1%</p>																								
	<p>Resistenza della superficie (scala MOHS) Scratch hardness (MOHS scale) Dureté de la surface (échelle MOHS) Oberflächenhärte (MOHS skala) Поверхностная прочность по (шкале Мооса)</p>	<p>EN 101</p>	<p>> 6</p>																								
	<p>Resistenza a flessione e forza di rottura Modulus of rupture and breaking strength résistance à la flexion et force de rupture Biegefestigkeit und Bruchlast Прочность на изгиб Модуль жесткости</p>	<p>S ≥ 1300 N R ≥ 35 N/mm2</p>	<p>S ≥ 1300 N R ≥ 35 N/mm²</p>																								
	<p>Resistenza alla abrasione della superficie di piastrelle smaltate Resistance to surface abrasion of glazed tiles Résistance à l'abrasion de la surface des carreaux émaillés Widerstand gegen Abrieb der Oberfläche der glasierten Fliesen Стойкость глазурованной плитки к поверхностному истиранию</p>	<p>Come dichiarato dal produttore See manufacturer's declaration Selon déclaration du producteur Entsprechend der Herstellerangaben Как указано изготовителем</p>	<table border="1"> <thead> <tr> <th></th> <th>white</th> <th>dark</th> <th>grey/sand taupe</th> </tr> </thead> <tbody> <tr> <td>Classe</td> <td>5</td> <td>3</td> <td>4</td> </tr> <tr> <td>Class</td> <td>5</td> <td>3</td> <td>4</td> </tr> <tr> <td>Classe</td> <td>5</td> <td>3</td> <td>4</td> </tr> <tr> <td>Gruppe</td> <td>5</td> <td>3</td> <td>4</td> </tr> <tr> <td>Класс</td> <td>5</td> <td>3</td> <td>4</td> </tr> </tbody> </table>		white	dark	grey/sand taupe	Classe	5	3	4	Class	5	3	4	Classe	5	3	4	Gruppe	5	3	4	Класс	5	3	4
	white	dark	grey/sand taupe																								
Classe	5	3	4																								
Class	5	3	4																								
Classe	5	3	4																								
Gruppe	5	3	4																								
Класс	5	3	4																								
	<p>Coefficiente di dilatazione termica lineare Linear thermal expansion coefficient Dilatation thermique linéaire Lineare Wärmeausdehnung Кoeffициент линейного теплового расширения</p>	<p>Come dichiarato dal produttore See manufacturer's declaration Selon déclaration du producteur Entsprechend der Herstellerangaben Как указано изготовителем</p>	<p>Metodo disponibile Method available Méthode disponible Verfügbares verfahren Определяется производителем</p>																								
	<p>Resistenza allo shock termico Thermal shock resistance Résistance au choc thermique Temperaturwechselbeständigkeit Стойкость к тепловым перепадам</p>	<p>Nessun campione deve presentare alterazioni No sample must show visible alteration Aucun carreau ne doit présenter d'altération Kein Muster darf sichtbare Veränderungen zeigen Никакой образец не должен показывать изменений</p>	<p>Resistente Resistant Résistant Widerstandsfähig Устойчивый</p>																								
	<p>Resistenza al gelo Frost resistance Résistance au gel Frostbeständigkeit Морозостойкость</p>	<p>Non devono presentare difetti visibili No sample must show visible defect Aucun carreau ne doit présenter de défaut Muster dürfen keine sichtbaren Schäden zeigen Не должны обнаруживать видимые дефекты</p>	<p>Ingelivo Frost proof Ingeif Froststichigkeit Морозостойкость</p>																								
	<p>Resistenza all'attacco chimico (tranne acido fluoridrico) Resistance to chemical attack (except hydrofluoric acid) Résistance à l'attaque chimique (sauf acide fluorhydrique) Säure- und Laugenbeständigkeit (außer Flußsäure) Стойкость к бытовым химикатам</p>	<p>Nessun campione deve presentare alterazioni No sample must show visible alteration Aucun carreau ne doit présenter d'altération Muster dürfen keine sichtbaren Veränderungen zeigen Никакой образец не должен показывать изменений</p>	<p>Classe A-HA-LA Class A-HA-LA Classe A-HA-LA Gruppe A-HA-LA Класс A-HA-LA</p>																								
	<p>Resistenza alle macchie di piastrelle smaltate Resistance to stains of glazed tiles Résistance aux taches des carreaux émaillés Widerstand gegen Fleckenbildner der glasierten Fliesen Стойкость глазурованной плитки к образованию пятен</p>	<p>Nessun campione deve presentare alterazioni No sample must show visible alteration Aucun carreau ne doit présenter d'altération Muster dürfen keine sichtbaren Veränderungen zeigen Никакой образец не должен показывать изменений</p>	<p>Classe 5 Class 5 Classe 5 Gruppe 5 Класс 5</p>																								
    	<p>B.C.R.A. REP. CEC. 6/81</p>	<p>0,40 ≤ f^N ≤ 0,74</p>	<p>R10 R11</p>																								
	<p>DIN 51130 ≥ R 9</p>	<p>R10 R11</p>	<p>Classe B Classe C Class B Class C Classe B Classe C Gruppe B Gruppe C Класс B Класс C</p>																								
	<p>DIN 51097</p>	<p>f^N ≥ 0,42</p>	<p>R10: Classe P3 Classe P4 Class P3 Class P4 Classe P3 Classe P4 Gruppe P3 Gruppe P4 Класс P3 Класс P4</p>																								
	<p>DCOF Pendulum Australiano AS 4586 Pendulum Britannico BS 7976</p>	<p>PTV > 36 wet</p>	<p></p>																								